

# Δ6 White Liner New

10.0

	110	3000	4000	5000	6000	8000
Silica	17	510	680	850	1020	1360
Kaolin	14	420	560	700	840	1120
Frit 3134	11	330	440	550	660	880
G. Borate	11	330	440	550	660	880
Whiting	8	240	320	400	480	640
Talc	13	390	520	650	780	1040
Nepheline Syenite	26	780	1040	1300	1560	2080
Zircopax	10	300	400	500	600	800

Notes:

With use this glaze developed darkened crazing lines.