

# Δ6 White Liner Mod1

10.1

	110	3000	4000	5000	6000	8000
Silica	24	720	960	1200	1440	1920
Kaolin	8	240	320	400	480	640
Frit 3134	11	330	440	550	660	880
G. Borate	11	330	440	550	660	880
Whiting	10	300	400	500	600	800
Talc	10	300	400	500	600	800
Nepheline Syenite	26	780	1040	1300	1560	2080
Zircopax	10	300	400	500	600	800

Notes:

Consider a titanium/tin/zirconium blend