

NSG (New Sage) Test

12.0

	100	96	104	94	100	100
Silica	19	19	19	19		
Kaolin (EPK)	16	16	16	10		
Frit 3134	19	19	19	19		
Potash Feldspar (Cluster)	28	28	28	28		
Talc	6	6	6	6		
Wollastonite	8	8	8	8		
Dolomite	4		8	4		
(KNa)O [0.1 to 0.3]	0.250	0.291	0.219	0.250		
MgO [0 to 0.3]	0.224	0.182	0.255	0.224		
CaO [0.2 to 0.6]	0.526	0.527	0.525	0.527		
ZnO [0 to 0.20]						
Al ₂ O ₃ [0.25 to 0.5]	0.352	0.408	0.309	0.280		
B ₂ O ₃ [0 to 0.3]	0.205	0.239	0.180	0.206		
SiO ₂ [0.25 to 0.4]	3.364	3.912	3.952	3.221		
Si:Al	9.57	9.58	9.55	11.49		

Notes:

Old Sage was colored with
 1% cobalt carbonate
 0.75% copper carbonate
 3% iron oxide (Spansih Red)
 6% rutile (milled)

Mix recipes #234, 2+3=1