


# Sr15 Test

13.0



|  | 100   | 95    | 105   | 100 | 100 | 100 |
|--|-------|-------|-------|-----|-----|-----|
| Silica                                       | 29    | 24    | 34    |     |     |     |
| Kaolin (EPK)                                 | 15    |       |       |     |     |     |
| Potash Feldspar (Cluster)                    | 10    |       |       |     |     |     |
| Whiting                                      | 5     |       |       |     |     |     |
| Nepheline Syenite                            | 10    |       |       |     |     |     |
| Frit 3134                                    | 16    |       |       |     |     |     |
| Strontium Carbonate                          | 15    |       |       |     |     |     |
| (KNa)O [0.1 to 0.3]                          | 0.231 |       |       |     |     |     |
| MgO [0 to 0.3]                               |       |       |       |     |     |     |
| CaO [0.2 to 0.6]                             | 0.395 |       |       |     |     |     |
| ZnO [0 to 0.20]                              |       |       |       |     |     |     |
| Al <sub>2</sub> O <sub>3</sub> [0.25 to 0.5] | 0.346 |       |       |     |     |     |
| B <sub>2</sub> O <sub>3</sub> [0 to 0.3]     | 0.193 |       |       |     |     |     |
| SiO <sub>2</sub> [0.25 to 0.4]               | 3.408 | 3.106 | 3.711 |     |     |     |
| Si:Al  | 9.85  | 8.98  | 10.71 |     |     |     |

**Notes:**

2% copper carbonate added

Tests were too thin for great analysis, #3 had an especially thin feel.

#1 good bright color response

#2 overall seemed much brighter and glossier.

#3 the one thick spot seemed to have defects in it. Hard to tell.