

BA10 v2 "Death by Chocolate"

14.1



	108	3000	4000	5000	6000	8000
Silica	20	600	800	1000	1200	1600
Kaolin (EPK)	8	240	320	400	480	640
Ball Clay (OM4)	7	210	280	350	420	560
Potash Feldspace (Cluster)	32	960	1280	1600	1920	2560
Talc	5	150	200	250	300	400
Gerstley Borate (Laguna)	8	240	320	400	480	640
Frit 3134	10	300	400	500	600	800
Bone Ash	10	300	400	500	600	800
Red Iron Oxide (synthetic)	8	240	320	400	480	640

Notes:

Semigloss, slight mottling of iron. Nice smooth finish.
Very opaque. Does not enhance textures.

A pleasant glaze but not what I was seeking.