

BA2 Iron-Rutile

14.3



BA2

Silica	20
Kaolin (EPK)	8
Ball Clay (OM4)	7
Potash Feldspace (Cluster)	32
Talc	5
Gerstley Borate (Laguna)	8
Frit 3134	10
Bone Ash	10

Iron Oxide (Spanish)	0, 3.3, 6.6, 10 top to bottom
----------------------	-------------------------------

Rutile	0, 1.3, 2.6, 4 left to right
--------	------------------------------

Only slight variations happened with these tests. The browns were slightly light as iron decreased but that is all.

The rutile-only test has a pleasant feel, color and glossy surface. It has the feel of wheat.