

	#1 (C)	#2 (D)	#3 (B)	
Silica	26		26	
Kaolin (EPK)	5	12	5	
Potash Feldspace (Cluster)	25		25	
Whiting	10		10	
Gerstley Borate (Laguna)	18		18	
Talc	9		9	
Zicronium (Zircopax)	10	10		
Copper Carbonate			2	
Notes:				

Notes:

The low EPK version is in the lower left. This test tile had the nicest finish. There was some micro pinholes in the high-alumina (EPK) copper tests.

The addition of a small amount of copper creates a rather nice cerelean blue. Try between 0.3 and 0.7.

The progress to a better white glaze will continue from recipe version #1.