



	B	C	D
Silica	26		
Kaolin (EPK)	5		
Potash Feldspace (Cluster)	25		
Whiting	10		
Gerstley Borate (Laguna)	18		
Talc	9		
Titanium Dioxide		9	9
Tin Oxide	5		5

Notes:

Test F, the result I was hoping for, is approximately 3.75 Sn and 9 Ti.

The other side of the till was whiter with a hint of pink. The glaze is pinker where thicker and breaks to a golden-tan yellow.