

Duck Egg

15.6

	105.8	3000	4000	5000	6000	8000
Silica	26	780	1040	1300	1560	2080
Kaolin (EPK)	5	150	200	250	300	400
Potash Feldspace (Cluster)	25	750	1000	1250	1500	2000
Whiting	10	300	400	500	600	800
Gerstley Borate (Laguna)	18	540	720	900	1080	1440
Talc	9	270	360	450	540	720
Tin Oxide	3.8	113	150	188	225	300
Titanium Dioxide	9	270	360	450	540	720
Chrome Oxide	0.02	0.3	0.4	0.5	0.6	0.8

Notes:

A range of Chrome Oxide can be from 0 to maybe 0.1. Further testing with a wider range of chrome is planned.

This glaze can have pink spots if the glaze is sieved before the addition of the chrome oxide. It varies with shades of pink, white, and gold possible. Pieces near other chrome glazes typically go to a pink-yellow sunrise.

This glaze has a very smooth feel making it well suited for a liner glaze in dinnerware.