

Nu-clear Test				16.0
	101 (B)	100 (C)	100 (D)	
Silica	25	27	27	
Kaolin (EPK)	15	15	17	
Frit 3134	20	20	20	
Potash Feldspar (Cluster)	20	16	10	
Talc	6	4	4	
Whiting	5	8	12	
Strontium Carbonate	10	10	10	
(KNa)O [0.1 to 0.3]	0.211	0.188	0.144	
MgO [0 to 0.3]	0.147	0.097	0.090	
CaO [0.2 to 0.6]	0.423	0.500	0.569	
SrO	0.219	0.215	0.196	
Al <sub>2</sub> O <sub>3</sub> [0.25 to 0.5]	0.288	0.262	0.231	
B <sub>2</sub> O <sub>3</sub> [0 to 0.3]	0.214	0.211	0.192	
SiO <sub>2</sub> [0.25 to 0.4]	3.132	2.981	2.567	
Si:Al	10.88	11.39	11.11	
Notes:				
<p>Mostly clear, still cloudy when thick. The results from the three recipes were not significantly different and none appeared more suitable as a clear recipe compared with any other version.</p> <p>This glaze was difficult to apply thickly.</p> <p>Version C was picked for another a Cu-Ni-Ti color test in 16.1</p>				