

## Δ6 Glossy Blue

2.2



	100	3000	4000	5000	6000	8000
Silica	19	570	760	950	1140	1520
EPK Kaolin	20	600	800	1000	1200	1600
Frit 3134	20	600	800	1000	1200	1600
Potash Feldspar (Cluster)	20	600	800	1000	1200	1600
Talc	6	180	240	300	360	480
Wollastonite	15	450	600	750	900	1200
Cobalt Carbonate	0.5 to 2	15-60	20-80	25-100	30-120	40-160
	1.2	36	48	60	72	96

### Notes:

Same base glaze as Clear.

Typically I make this glaze by pouring clear and adding an approximate amount of cobalt carbonate.

My target amount is 1.2% cobalt carbonate.

Intensity of glaze varies with amount of cobalt carbonate added. Amounts up to 5% can be added for a very rich (and expensive) royal blue.

Mostly transparent and generally enhances textures when thin.