

Δ6 Fake Korean Celadon

2.3



	101.6	3000	4000	5000	6000	8000
Silica	11	330	440	550	660	880
EPK Kaolin	13	390	520	650	780	1040
G. Borate	30	900	1200	1500	1800	2400
Potash Feldspar (Cluster)	46	1380	1840	2300	2760	3680
Copper Carbonate	0.6	18	24	30	36	48
Bentonite	1	30	40	50	60	80

Notes:

May craze on some clay bodies.

Color is a pale olive green, very transparent with enhancement of light textures.

Cobalt and iron oxides will bleed.

Excellent over black or blue slip sgraffito work.