

## Δ6 Dark Olive

2.5



	97.5	3000	4000	5000	6000	8000
Silica	15	450	600	750	900	1200
EPK Kaolin	5	150	200	250	300	400
G. Borate	20	600	800	1000	1200	1600
Potash Feldspar (Cluster)	20	600	800	1000	1200	1600
Nepheline Syenite	20	600	800	1000	1200	1600
Dolomite	2	60	80	100	120	160
Wollastonite	10	300	400	500	600	800
Red Iron Oxide	2.0	60	80	100	120	160
Titanium Dioxide	1.0	30	40	50	60	80
Cobalt Carbonate	0.5	15	20	25	30	40
Copper Carbonate	2.0	60	80	100	120	160

**Notes:**

Original recipe from lakesidepottery.com, some changes have been made.

Rutie blue when thick.

Enhances textures. Even leaf prints have shown through with great detail.

Can flow or drip but cleans up well.

May not be within functional limits. crazing can be seen on many pieces.