

Δ6 Tangerine

2.7



	115	3000	4000	5000	6000	8000
Silica	25	750	1000	1250	1500	2000
Kaolin (EPK)	11	330	440	550	660	880
Potash Feldspar (Cluster)	33	990	1320	1650	1980	2640
G. Borate	5	150	200	250	300	400
Whiting	24	720	960	1200	1440	1920
Tanerine MS #6027	15	450	600	750	900	1200
Bentonite	2	60	80	100	120	160

Notes:

Original recipe from Christa Assad

Good for small accents

Customers love it and potters hate it.

Not reactive.

Doesn't enhance textures