

# Zinc Blue

2.8



	100	3000	4000	5000	6000	8000
Silica	23	690	920	1150	1380	1840
EPK Kaolin	3	90	120	150	180	240
G. Borate	13	390	520	650	780	1040
Potash Feldspar (Cluster)	47	1410	1880	2350	2820	3760
Zinc Oxide	4	120	160	200	240	320
Dolomite	4	120	160	200	240	320
Whiting	6	180	240	300	360	480
Rutile	2.0	60	80	100	120	160
Copper Carbonate	0.5	15	20	25	30	40
Cobalt Carbonate	0.75	22.5	30	37.5	45	60
Bentonite	2.0	60	80	100	120	160

Notes:

Could benefit from a higher quality Kaolin.  
 Semi-gloss finish  
 Very opaque, tends to hide texture.