

Chocolate Matte

3.3



	100+15	3000	4000	5000	6000	8000
Silica	30	900	1200	1500	1800	2400
Kaolin (EPK)	5	150	200	250	300	400
G. Borate	21	630	840	1050	1260	1680
Feldspar (Potash)	17	510	680	850	1020	1360
Talc	17	510	680	850	1020	1360
Frit 3134	10	300	400	500	600	800
Red Iron Oxide	15	450	600	750	900	1200
Bentonite	2	60	80	100	120	160

Notes:

Based on "Reader's Digest Red"

Under my firing and cooling, a thin application is a rich brown with visible iron. Leach test came back fine.

May benefit from synthetic red iron oxide.

Sometimes this glaze blooms into the most interesting spectrum of color. Most of the time it remains a dark matte color

There has been some issues with crater-like blisters