

Melting Glacier 2.0

4.2



	92+4	3000	4000	5000	6000	8000
Silica	33	990	1320	1650	1980	2640
Kaolin (EPK)	6	180	240	300	360	480
G. Borate	10	300	400	500	600	800
Frit 3134	6	180	240	300	360	480
Talc	7	210	280	350	420	560
Whiting	6	180	240	300	360	480
Nepheline Syenite	18	540	720	900	1080	1440
Potash Feldspar (Cluster)	6	180	240	300	360	480
Copper Carbonate	1	30	40	50	60	80
Tin Oxide	3	90	120	150	180	240

Notes:

EPK changed from 14 to 6

This glaze has not been functioning well. Very sensitive to thickness of application. When too thick the glaze pits. This recipe is not being continued at Valley Pottery