

PMgO (Magnesium Purple) Test



P5

Silica	31
--------	----

Kaolin (EPK)	10
--------------	----

Nepheline Syenite	21
-------------------	----

Whiting	11
---------	----

G. Borate	19
-----------	----

Talc	8
------	---

4.2 Tin Oxide 0.15 Chrome premix	2, 4, 6, 8 left the right
-------------------------------------	---------------------------

Cobalt Carbonate	0.25, 0.5, 0.75, 1 top to bottom
------------------	----------------------------------

Notes:

Top left, no colorants added. Surface is a milky satin matte
 Across: 2, 4, 6, 8 of (4.2 Tin Oxide : 0.15 Chrome Oxide premix)
 Down: 0.25, 0.5, 0.75, 1.0 of Cobalt Carbonate

My preference was for (4 Tin+Chrome, 1 Cobalt) and (4 Tin+Chrome, 0.25 Cobalt)

This is the same base as "White Lilac" which is colored with just 4 Tin+Chrome. A more pronounced lilac could be made with ~0.1 Cobalt added to it.