

# Snowy Lilac

5.3



	104.25	3000	4000	5000	6000	8000
Silica	31	930	1240	1550	1860	2480
Kaolin (EPK)	10	300	400	500	600	800
Nepheline Syenite	21	630	840	1050	1260	1680
Whiting	11	330	440	550	660	880
G. Borate	19	570	760	950	1140	1520
Talc	8	240	320	400	480	640
<i>Chrome Oxide</i>	<i>0.15</i>	<i>4.5</i>	<i>6</i>	<i>7.5</i>	<i>9</i>	<i>12</i>
Tin Oxide	4	120	160	200	240	320
Cobalt Carbonate	0.1	3	4	5	6	8

**Notes:**

Has been an excellent buttery purple hue light grey. Reacts well with other glazes, especially the related Purple glaze.

This recipe was a modification of Purple to bring the recipe to be within the limits and also add a source of magnesium.

This glaze smooths over textures.

New batch was made without the addition of chrome oxide. This change appears to have removed some of the grey hue.