


"Snowy Lilac" Base (copper-tin) Test

5.4



Base	
Silica	31
Kaolin (EPK)	10
Nepheline Syenite	21
Whiting	11
G. Borate	19
Talc	8
Tin oxide	0.75, 1.5, 2.25, 3.0 top to bottom
Copper Carbonate	0.75, 1.5, 2.25, 3.0 left to right
Notes:	
Top left, no colorants added. Surface is a milky satin matte This is the same base as "Snowy Lilac" which is colored with just 4 Tin, 0.1 cobalt carbonate.	
Overall this test was not exciting. The left variation (0.75 copper) show good qualities for a cerulean blue.	