

Whiskey River

6.3



	109	3000	4000	5000	6000	8000
Silica	18	540	720	900	1080	1440
Kaolin (EPK)	8	240	320	400	480	640
Ball Clay (OM-4)	7	210	280	350	420	560
Potash Feldspar (Cluster)	32	960	1280	1600	1920	2560
Whiting	5	150	200	250	300	400
G. Borate	8	240	320	400	480	640
Frit 3134	10	300	400	500	600	800
Talc	7	210	280	350	420	560
Strontium Carbonate	5	150	200	250	300	400
Iron Oxide	6	180	240	300	360	480
Rutile (milled)	3	90	120	150	180	240

Notes:

Stable base glaze. Hasn't run on its own.

Dark carmel base with floating light blue.

Breaks on texture.

Consider using high grade iron or increasing the amount by 1%