


“Snowy Lilac” Base (copper-tin) Test



Base

Silica	31
Kaolin (EPK)	10
Nepheline Syenite	21
Whiting	11
G. Borate	19
Talc	8
Tin oxide	0.75, 1.5, 2.25, 3.0 top to bottom
Cobalt Carbonate	0.75, 1.5, 2.25, 3.0 left to right

Notes:

Top left, no colorants added. Surface is a milky satin matte

This is the same base as “Snowy Lilac” which is colored with just 4 Tin, 0.1 cobalt carbonate.

Overall this test was not exciting. The left variation (0.75 copper) show good qualities for a cerulean blue.