

Liquid Earth

7.2



	108	3000	4000	5000	6000	8000
Silica	18	540	720	900	1080	1440
Wollastonite	15	450	600	750	900	1200
Potash Feldspar (Cluster)	30	900	1200	1500	1800	2400
Ball Clay (OM4)	10	300	400	500	600	800
Zinc Oxide	11	330	440	550	660	880
Nepheline Syenite	4	120	160	200	240	320
G. Borate	12	360	480	600	720	960
Rutile (milled)	4	120	160	200	240	320
Cobalt Carbonate	0.5	15	20	25	30	40
Copper Carbonate	1.0	30	40	50	60	80
Red Iron Oxide (Spanish)	2.5	75	100	125	150	200

Notes:

Slight dripping when too thick.
 Reacts nicely over Tenmoku glaze.