

Sage

9.0



	100	3000	5000	8000
Silica	18.5	555	925	1480
Kaolin	20	600	1000	1600
Frit 3134	20	600	1000	1600
Potash Feldspar	20	600	1000	1600
Talc	11.5	345	575	920
Wollastonite	10	300	500	800
Cobalt Carbonate	1.0	30	50	80
Copper Carbonate	0.75	22.5	37.5	60
Red Iron Oxide	3.0	90	150	240
Rutile	6.0	180	300	480

Notes:

Glossy, speckled green on white clay.

Brown to floating blue over iron.

Breaks brown with texture.

This was an excellent glaze in New Zealand but had issues at VPA. It frequently blistered at the bottoms of pieces. The verigations and beauty where only found when a thin line was applied over Tenmoku. Discontinued.