

Zinc Blue



	100	3000	5000	8000
Silica	23	690	1150	1840
EPK Kaolin	3	90	150	240
G. Borate	13	390	650	1040
Potash Feldspar (Cluster)	47	1410	2350	3760
Zinc Oxide	4	120	200	320
Dolomite	4	120	200	320
Whiting	6	180	300	480
Rutile	2.0	60	100	160
Copper Carbonate	0.5	15	25	40
Cobalt Carbonate	0.75	23	37	60
Bentonite	2.0	60	100	160

Notes:

Could benefit from a higher quality Kaolin.
Semi-gloss finish
Very opaque, tends to hide texture.